



Multi Crystalline Silicon Solar PV Cells



RIPL production processes are automated from the incoming silicon wafer inspection/classification to the final cell sorting. The surface of **RESERV 626** cells are processed through acid texturization and have an isotropically textured surface. The cells are manufactured and tested for optimum performance and processing characteristics. Our Quality Control systems include checking every cell for mechanical faults, apart from electrical performance.

Cell Layout





Specifications are in mm

Features

Product	Multi Crystalline Silicon Solar Cell	\sim	High Conversion Efficiency		
Substrate	P-type Multi Crystalline Silicon Wafer				
Device Structure	n+/p/p+	O	Good Color Uniformity		
Dimensions	Size: 156.75mm x 156.75mm ± 0.25mm	126	Statistical Process Control		
	Average Thickness: 200 ± 20μm	7_0			
Front	Blue Anti-Reflective Coating	100 % FLY	On the fly 100 % EL testing		
	(Silicon Nitride) Acid textured surface	RD	5 1:1 202		
	0.6 ± 0.1 mm Silver bus bars		Focused in house R & D		
	Negative pole (-)	(ISO)	ISO 9001, OHSAS 18001		
Back	Full-surface Aluminum BSF 0.15 ± 0.1 mm Silver bus bars		certificated		
			PID Free		
	Positive pole (+)		FIDFIEE		



Multi Crystalline Silicon Solar PV Cells


RESERV 626 Series L1

Electrical Data *


Part No	Class	Efficiency Range (%)	Rated Power (Wp)	Max. Power Current Impp (A)	Short Circuit Current Isc (A)	Max. Power Voltage V _{mpp} (V)	Open Circuit Voltage Voc (V)	Fill Factor (%)
RESERV-626L1-1900	190	19.00 - 19.20	4.67	8.55	8.97	0.546	0.639	81.45
RESERV-626L1-1880	188	18.80 - 19.00	4.63	8.52	8.95	0.543	0.637	81.15
RESERV-626L1-1860	186	18.60 - 18.80	4.58	8.49	8.93	0.539	0.636	80.57
RESERV-626L1-1840	184	18.40 - 18.60	4.53	8.43	8.90	0.537	0.633	80.35
RESERV-626L1-1820	182	18.20 - 18.40	4.47	8.41	8.88	0.532	0.629	80.10
RESERV-626L1-1800	180	18.00 - 18.20	4.43	8.40	8.85	0.527	0.626	79.90
RESERV-626L1-1780	178	17.80 - 18.00	4.38	8.35	8.83	0.524	0.624	79.41
RESERV-626L1-1760	176	17.60 - 17.80	4.33	8.32	8.81	0.520	0.621	79.08

^{*} Standard test Conditions: AM 1.5, 1000 w/m², 25° C (Accuracy is ± 1.5% rel.)

IV Curve



Spectral Response



Temperature Coefficients

Voltage: - 0.3190 % / K

Current: + 0.0485 %/ K

Power: - 0.3854 % / K

Process Recommendation

Solder Joint: Copper ribbons coated with 15-30 μm of Sn / Pb (60% / 40%). Soldering results may differ due to different flux, ribbons, soldering methods and parameters.

RenewSys India Private Limited, Plot # 6, Survey # 114/P, Fab City, Sri Nagar Village, Maheswaram Mandal, Hyderabad, India - 501 359 Tel: +91- 40-6730 3000; Email: renewsys@renewsysindia.com; Web: www.renewsysworld.com